



TÜVRheinland®

DIN CERTCO

Precisely Right.



Certification Scheme

Products made of compostable materials (DIN-Geprüft)

according to

DIN EN 13432

if applicable, in connection with

DIN EN 14995

ISO 17088

ISO 18606

AS 4736

(Edition: October 2017)

DIN CERTCO • Alboinstrasse 56 • 12103 Berlin

Tel: +49 30 7562-1131 • Fax: +49 30 7562-1141 • E-mail: info@dincertco.de • www.dincertco.de

Foreword

DIN CERTCO was founded in 1972 by DIN Deutsches Institut für Normung e. V. (German Institute for Standardization) for the awarding of DIN marks and provides certification for products, persons, services and companies on the basis of DIN standards and similar specifications.

In order to prove our impartiality, independency and competence, we are voluntary accredited according to DIN EN ISO/IEC 17065. For the satisfaction and trust of our clients and their data, we maintain furthermore a certified

- Quality Management System according to DIN EN ISO 9001
- Environmental Management System according to DIN ISO 14001
- Information Security Management System according to DIN ISO/IEC 27001
- Occupational Health and Safety Management System according to OHSAS 18001

The "Products made of compostable materials (DIN-Geprüft)" certification scheme was created in collaboration with the DIN CERTCO "Biodegradable Materials" certification committee (ZA-BAW in its German abbreviation) and will be continuously refined. It makes a distinction between the certification of materials and intermediates and the certification of (end) products.

In addition to DIN CERTCO's general terms and conditions, this certification scheme provides a basis for parties who provide products made of compostable materials to label their products with the compostability mark, the "DIN-Geprüft Industrial Compostable"-logo. This documents that their products fulfil all DIN EN 13432 requirements as well as, if applicable, the additional/simultaneous requirements in DIN EN 14995, ISO 17088, ISO 18606 and/or AS 4736.

The "DIN-Geprüft"-mark creates trust among consumers that a neutral and competent entity carefully inspected and evaluated test criteria. DIN CERTCO's regular monitoring additionally ensures that product quality remains intact, even when production is running. Thus, customers receives added value that they can take into consideration when making purchase decisions.

Products made of compostable materials are given the right to use the compostability mark "DIN-Geprüft Industrial Compostable" upon fulfilling the requirements indicated under Section 4 according to the procedure described in this certification scheme. For materials or intermediates a certificate is issued if the requirements named under Section 4 are fulfilled.

All certificate holders can be viewed on the daily up-dated homepage of DIN CERTCO (www.dincertco.de).

Amendments

The following amendments have been made to the „Products made of compostable materials (DIN-Geprüft)“ (2015-06) certification scheme:

- a) Deletion of certification standard ASTM D 6400

Earlier versions

Certification scheme „Products made of compostable materials (DIN-Geprüft)“ (2015-06)

Certification scheme „Products made of compostable materials (DIN-Geprüft)“ (2014-08)

Certification scheme „Products made of compostable materials (DIN-Geprüft)“ (2013-02)

Remark

The German version of this certification scheme shall be taken as authoritative. No guarantee can be given to the English translation.

CONTENTS

1	Scope	5
2	Test and certification specifications.....	5
3	Definitions	6
4	Product requirements	7
5	Testing	8
5.1	General information.....	8
5.2	Types of tests.....	8
5.2.1	Initial test (Type testing).....	8
5.2.2	Verification test (Control test).....	9
5.2.3	Supplementary testing.....	9
5.2.4	Special test.....	9
5.3	Sampling	9
5.4	Test procedure.....	10
5.5	Test report.....	10
6	Certification	11
6.1	Application for certification	11
6.2	Required tests/documents.....	12
6.2.1	Manufactured items consisting of items not yet registered/certified	12
6.2.2	Manufactured items composed of materials already registered (Blends).....	13
6.2.3	Manufactured items consisting of natural organic substances	14
6.2.4	Manufactured items consisting of paper/recycled paper	15
6.2.5	Manufactured items composed of registered materials and materials indicated in Section A	17
6.2.6	Manufactured items with coatings.....	18
6.2.7	Manufactured items consisting of multiple layer structures made of registered materials	21
6.2.8	Manufactured items exceeding the maximum registered/certified layer thickness	23
6.2.9	Manufactured items consisting of manufactured items already registered/certified and non-biodegradable additives	23
6.2.10	Special cases for Products/Intermediates	27
6.3	Confirmations of acceptability for manufactured items.....	27
6.4	Definition of types, subtypes and manufactured item families.....	28
6.5	Sub-licences	29
6.5.1	Sub-licences and without self-production.....	29
6.5.2	Sub-licences for production facilities.....	29
6.6	Confidentiality	30
6.7	Conformity assessment.....	30
6.8	Registration numbers of products, materials, intermediates and confirmations of acceptability	30
6.9	Certificate and the right to use the mark for (end)products	30
6.10	Publication	31

6.11	Validity of certificates and confirmations of acceptability	31
6.12	Renewal of certificates and confirmations of acceptability	32
6.13	Expiration of certificates and confirmations of acceptability	32
6.14	Alterations/Amendments	32
6.14.1	Alteration/Amendment to a product, intermediate or material	32
6.14.2	Alterations to the basic test specifications.....	33
6.15	Defects in products, intermediates, materials	33
7	Surveillance	34
7.1	General	34
7.2	Surveillance by the manufacturer	34
7.3	Surveillance by DIN CERTCO	34
7.4	Verification tests (Control tests).....	34
7.4.1	Products	34
7.4.2	Materials/Intermediates	35
7.5	Assessment of verification test (Control test).....	36
7.5.1	General	36
7.5.2	Design requirements	36
7.5.3	Spectra (Identification of material)	36
7.5.4	Complaints	36
A	Fillers, colours and processing auxiliaries	37
B	Tests.....	39
C	Infrared transmission spectrum.....	46

1 Scope

This certification scheme applies for (end) products made of compostable materials or intermediates, and, in connection with the testing foundations named below, contains all requirements on issuing the compostability mark "DIN-Geprüft Industrial Compostable".

This certification scheme establishes requirements that need to be met by the product, material or intermediate directly, as well as requirements relating to the associated testing, monitoring and certification.

If an (end) product, material or intermediate demonstrates conformity to the criteria specified in this certification scheme, then a certificate will be issued for that product. Furthermore, these certificates will be added to the corresponding lists of certificate holders (see Section 6.10). The same applies to confirmations of acceptability according to Section 6.3.

There is no legal right to receiving a certificate or any other confirmation of conformity.

2 Test and certification specifications

The following referenced documents are the basis for testing and certification. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

Products, intermediates and materials can be certified and/or registered according to the following standards (certification standards):

DIN EN 13432	Requirements for packaging recoverable through composting and biodegradation
DIN EN 14995	Plastics - Evaluation of compostability - Test scheme and specifications
ISO 17088	Specifications for compostable plastics
ISO 18606	Packaging and environment - Organic recycling
AS 4736	Biodegradable Plastics – Biodegradable Plastics suitable for Composting and other microbial Treatment

Product, intermediates and materials are required to demonstrate compliance with the requirements of DIN EN 13432. One/several of the standards named may additionally be covered by the certification.

Laboratory testing must be performed according to the stipulations in the standards named above according to the following standards or test methods (testing standards):

DIN EN ISO 14851	Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium - Method by measuring the oxygen demand in a closed respirometer
DIN EN ISO 14852	Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium - Method by analysis of evolved carbon dioxide

DIN EN ISO 14855-1	Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions -- Method by analysis of evolved carbon dioxide -- Part 1: General procedure
DIN EN ISO 14855-2	Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions -- Method by analysis of evolved carbon dioxide -- Part 2: Gravimetric measurement of carbon dioxide evolved in a laboratory-scale test
ASTM D 5338	Standard Test Method for Determining Aerobic Biodegradation of Plastics Materials Under Controlled Composting Conditions
ISO 16929	Plastics - Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test
DIN EN 14045	Packaging - Evaluation of the disintegration of packaging materials in practical oriented tests under defined composting conditions; German version EN 14045:2003
DIN EN 14046	Packaging - Evaluation of the ultimate aerobic biodegradability of packaging materials under controlled composting conditions - Method by analysis of released carbon dioxide"; German version EN 14046:2003
DIN EN ISO 10634	Water quality – Guidance for the preparation and treatment of poorly water-soluble organic compounds for the subsequent evaluation of their biodegradability in an aqueous medium
ASTM E 1676	Standard Guide for conducting Laboratory Soil Toxicity or Bioaccumulation Tests with the Lumbricid Earthworm <i>Eisenia fetida</i> and the Enchytraeid Potworm <i>Enchytraeus albidus</i>
AS 4454	Composts, soil conditioners and mulches
OECD 208	Terrestrial Plant Test: 208: Seedling Emergence and Seedling Growth Test

Federal Quality Association Compost (ed.): Manual of methods for analysing organic
(Bundesgütegemeinschaft Kompost e.V. (Hrsg.)) fertilisers, soil improver and substrates

- this certification scheme
- the general terms and conditions of DIN CERTCO
- the schedule of fees in its most current version

The obligation to comply with laws and regulations governing the respective products is in no way affected by this certification scheme.

3 Definitions

For the purposes of this certification scheme, the following definitions shall apply:

Additive	Substances and product constituents added to a product, material or intermediate in order to, for example, generate certain properties (e.g. adhesives, antiblocking agents, printing inks).
----------	--

Blank compost	Compost obtained from a parallel process according to B 3 without addition of sample material
Blend	Physical mixture of 2 or more materials without reactive process.
Certification	Proof of conformity with the requirements of the named standards as well as with this certification scheme for final products. A licence to use the mark is granted.
Compostable material	Material meeting the requirements of this certification scheme. The classification of types shall be made according to Section 6.4.
Continuous phase	The background phase (polymer 1) of a multiphase system with at least one further phase (polymer 2) (e.g. blend). A blend always has two phases: a continuous phase and the dispersed phase.
Intermediate	Semi-finished item. Optional state between material and product, e.g. laminates consisting of several layers of material. The classification of types shall be made according to Section 6.4.
Manufactured item	Material, intermediate or product according to this certification scheme. The classification of types shall be made according to Section 6.4.
Material	Material that is (in case of polymers) primarily based on organic chain molecules and used, for example, to manufacture intermediates or products. Materials generally contain further inorganic or low molecular weight organic materials used to influence processing or application properties. Materials can also consist of materials other than plastics.
Product	Article that is disposed of as waste (for composting) after use, is manufactured from polymeric materials or intermediates and frequently also contains additives. Products are not necessarily packaging. The classification of types shall be made according to Section 6.4.
Production facility	Location at which production of manufactured items is carried out according to this certification scheme. This is not necessarily identical to the certificate holder's address.

4 Product requirements

According to the requirements of the underlying standards, the requirements named in the following must be fulfilled. Section 6 describes the details on providing the associated evidence.

- Compliance with the threshold values named in Table A.1 in DIN EN 13432.
- Complete biodegradability (90 % absolute biodegradation, or 90 % with a suitable reference substrate within not more than 6 months). Evidence must be proven via a test according to the standards named under Section 2.

- After composting for no more than 12 weeks, no more than 10 % of the tested material's original dry weight may be found in a > 2mm screen fraction. Evidence must be demonstrated via a test according to the standards named under Section B 3 (disintegration testing).
- The germination rate and plant biomass of both plant types grown on the compost using test substance must be higher than 90 % of the corresponding blank compost. Evidence must be demonstrated via a test according to the standards named under Section B 3.
- Additives present in a manufactured item at concentrations less than 1 % of mass item must be harmless for the composting process.
- The total sum of the organic compounds for which biodegradability need not be determined may not exceed 5 % of mass.
- Residues remaining in packaging or substances that may be dispatched along with the product must be suitable for composting.
- For the application of ISO 18606, ISO 17088: For organic additives present in a manufactured item at concentrations of 1 % to 10 % of mass referred to the manufactured item, the complete biodegradability must be evidenced separately. This evidence can be proven via a certification/notification of registration according to the certification scheme "Additives according to EN 13432" or "Products made of compostable materials". For the application of AS 4736 the testing of the manufactured item on ultimate biodegradability is required additionally.
- For the application of AS 4736 additionally: The survival rate and the mean weight of the applied worm specie exposed with the compost using test substance must be higher than 90 % of the corresponding blank compost. Evidence must be demonstrated via a test according to the standard named under Section B 3.4 Determining compost quality (earthworm toxicity test).

5 Testing

5.1 General information

To carry out the inspections and tests necessary for the evaluation and certifications, DIN CERTCO uses test laboratories it has recognised.

If applicable test reports according to the certification scheme "Products made of compostable materials" (Seedling), "Products made of compostable materials for home and garden composting" and "Additives which are harmless for the composting process" can be accepted.

All documents must be submitted in German or English.

5.2 Types of tests

5.2.1 Initial test (Type testing)

The initial test is a type test intended to establish whether the (end) product, intermediate, or material meets the requirements according to Section 4 of this certification scheme.

Section 6.2 shows which tests are necessary for individual cases.

5.2.2 Verification test (Control test)

Verification testing is performed on products, materials and intermediates.

Verification testing is performed in recurring, predefined intervals and establishes whether the certified (end) product, a registered material, a registered intermediate and/or a registered additive in production phase corresponds to the product tested during initial certification.

This must be evidenced on schedule via a test report with positive results from a testing laboratory recognised by DIN CERTCO.

Test reports are assessed by DIN CERTCO.

For this purpose, 5 samples of the certified/registered manufactured item are obtained from manufacturers' production facilities and provided to DIN CERTCO free of charge.

In the case of multiple certifications of the same manufactured item in the field of compostable materials at DIN CERTCO one evidence of a verification test per manufactured item is sufficient.

5.2.3 Supplementary testing

Supplement testing is performed when supplements, expansions or additions (see Section 6.14) are intended for a certified/registered manufactured item that may have an influence on conformity with the underlying requirements.

The type and scope of supplementary testing will be determined by DIN CERTCO in individual cases in coordination with the assessment committee.

5.2.4 Special test

A special test is conducted when

- defects are detected
- the production has been suspended for a period of more than 6 months
- required by DIN CERTCO - reasons to be specified
- requested in writing by a third party if a particular interest in the maintenance of proper conduct of market procedures in relation to competition or quality is involved.

The type and scope of special test will be determined by DIN CERTCO in each individual case, where applicable in coordination with the assessment committee.

If defects are detected in a special test, or if a special test is performed due to a stop in production, then the certificate holder shall bear the costs of the examination procedure.

Should the special test at the request of a third party reveal no defects, the costs shall be borne by said third party.

5.3 Sampling

The samples used for initial, verification and renewal testing are usually delivered by the manufacturer to the testing laboratory which has been commissioned to perform the tests. The manufacturer bears the associated costs.

The number of samples required for product testing is agreed between DIN CERTCO and the testing laboratory unless it is already specified in the applicable test standards.

5.4 Test procedure

Testing universally must be performed according to one or more of the standards named above.

According to standards DIN EN 13432, DIN EN 14995, ISO 17088, ISO 18606 and AS 4736 the following tests are required:

- Chemical characterisation according to Section B 1.
- Testing of complete biodegradability according to Section B 2.
- Testing of compostability under practice-relevant conditions (disintegration) and of the quality of the composts (ecotoxicity). Certification is made with the maximum layer thickness determined in testing according to Section B 3.
- Testing of soil toxicity under practice-relevant conditions (earthworm toxicity test) according to Section B 3.5 (only required if AS 4736 shall be applied).
- Additionally, for identifying the material it is necessary to perform an IR spectrum in accordance with Section C.

5.5 Test report

The testing laboratory informs the client of the test results by means of a test report. An original copy of it shall be submitted to DIN CERTCO; or a digital copy sent by the testing laboratory.

As a rule, the test report may not be older than 6 months at the time of application. In individual cases, older test reports can be recognised if the testing laboratory confirms the validity of the results by means of a test report in writing and the manufacturer confirms that the product/material/intermediate has not been changed since testing. Test reports that are more than 5 years old can generally no longer be recognised.

The test report must correspond to DIN EN ISO/IEC17025, Section 5.10 and must at least contain the following information:

- Name and address of the manufacturer
- Name and address of the applicant (if different than manufacturer)
- Test basis (standards and certification scheme) with date of issue
- Type of test (e.g. type test, additional test, etc.)
- Test date
- Results and evaluation of test
- If testing is being performed in parallel with multiple replicates, then the individual results must also be shown.
- Name and signature of the individual responsible for the test

6 Certification

Certification in the sense of this certification scheme relates to the assessment of conformity of a (end) product, intermediate or material by DIN CERTCO on the basis of test reports submitted by testing laboratories recognized by DIN CERTCO. In doing so, the (end) products being certified and/or intermediates or materials being registered for conformity with the requirements named in Section 4 are examined and subsequently monitored. Since this certification scheme is a modular system, the individual testing requirements are indicated accordingly in Section 6.2.

For registered materials and intermediates the right to use the logo is only granted to the certificate holder for **marketing and advertisement reasons**, not for labelling the product itself. A registration number is issued upon granting the certificate.

References to manufactured items that have already been registered/certified can minimise testing expenditures. The points named in the following shall apply.

Should a reference be made to an (end)product that has already been certified, then an additional agreement will be required from the certificate holder. References to certified products will only be possible if concerning an identical product. Thus, for the certification of e.g. trays a reference can be made to certified trays but not to certified carrier bags.

6.1 Application for certification

Applicants can be both manufacturers according to Article 4 of the Produkthaftungsgesetz (ProdHaftG) [German Product Liability Act] or retailers who market the products independently within the meaning of the Produkthaftungsgesetz with the written consent of the certificate holder.

The following documents must be submitted by the applicant to DIN CERTCO:

- The original application for certification, with a legally binding signature and company stamp.
- Completed datasheet (part of the application form).
- List of production facilities, including complete address. If production is being carried out by companies other than the certificate holder, then the company's complete name and address must be submitted. Production can be carried out at various locations alternatively or simultaneously. In this case, all alternative production facilities must be reported to DIN CERTCO upon application.
- Material Safety Data Sheets according to REACH for all substances being used to determine additives' suitability for composting (e.g. processing auxiliaries, printing inks, etc).

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- If required, an up-to-date test report according to Section 5.5 (see Section 5.2.1 and Section 6.2), when the test has not been contracted by DIN CERTCO within the scope of an ongoing certification process.
- Details on construction and layer thickness, if applicable.

- Density or grammage, if applicable, e.g. for paper and expanded item.
- Drawings, with data on all wall and layer thicknesses (d_{\max}), if applicable.
- Test report on an infrared transmission spectrum according to Section C.

Additionally for products:

- Information on intended use.
- Submitting of product samples.
- List of substances which in the course of intended use may be disposed of as waste along with the product (e.g. residual packaging contents).
For each substance: Proof of suitability for biological waste processing, e.g. reference to published data, according to internationally recognised standards and/or guidelines (e.g. OECD) dealing with biodegradability and toxicological effects of the substance.
- Food contents will be accepted in any case.

After receipt of the application, the applicant will receive a confirmation of order from DIN CERTCO with a procedure number and information on further processing.

6.2 Required tests/documents

Depending on the composition of the (end) products being certified and/or the intermediates or materials being registered, the tests named in the following will be required.

If assessment is finished with positive results and a positive decision is made regarding the application, the certification will be issued for the maximum layer thickness determined via testing according to Section B 3 and published according to Section 6.10.

The testing requirements for products, materials or intermediates are basically identical. Therefore, the requirements named in the following apply for all manufactured items equally. Depending on composition and structure of the manufactured item, a combination of the requirements named may become necessary.

6.2.1 Manufactured items consisting of items not yet registered/certified

If certification is being requested for a manufactured item consisting of a material that is not yet registered/certified, the following documents and information must be submitted along with the application form.

- a) Disclosure of chemical composition (including substances at concentrations below 1 % of mass).
- b) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- c) Test report on the chemical characterisation as specified in Section B 1.
- d) Test report on testing of ultimate biodegradability as specified in Section B 2.
- e) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather earthworm toxicity test).
- f) An infrared transmission spectrum in accordance with Section C.

6.2.2 Manufactured items composed of materials already registered (Blends)

If certification is being requested for a manufactured item consisting solely of materials already on the list according to Section 6.10 and no further additives are used, the following documents and information must be submitted along with the application form:

- a) List of the materials used, including information on mass portions.
- b) Test reports on testing compostability under practice-relevant conditions (disintegration) as specified in Section B 3.
- c) An infrared transmission spectrum in accordance with Section C.

Disintegration according b) can be omitted if the applied thickness of the blend made of two registered materials does not exceed the applied thickness of the respective registered material with the lower applied thickness.

6.2.2.1 Special rules

The following special rules apply on the precondition that the compostable properties (disintegration) of blends are determined by the properties of the continuous phase. They only refer to the certification of ranges. The mixtures used for the testing needs to be defined in cooperation with DIN CERTCO and the testing laboratory. It needs to be representative for the continuous phase. As long as the continuous phase remains identical, different mixture proportions have no influence on compostability. The applicant must provide evidence and data on the respective continuous phase.

The maximum layer thickness will be defined depending on the layer thicknesses tested.

Blend of materials from identical material groups:

For blends of registered materials that are only distinguished by molecular weight, the disintegration test according to Section B 3 can be omitted. The requisite for this is that the manufacturing process for the materials is identical and there is certification with the same manufacturer. The maximum layer thickness is that of the material with the lowest determined layer thickness. The condition for this is that any additives used in producing the manufactured item do not cause any chemical or structural changes.

Ranges in blends made from 2 different materials:

It is possible to register composition ranges of two different materials (A and B) that have already been registered. Doing so requires disintegration tests of the various compositions and continuous phases (e.g. ratio A/B of 20/80 and 80/20).

Provided that the range within the blend remains inside a certain threshold, some of the tests may be omitted. This must be determined in coordination with DIN CERTCO and, if applicable, the testing laboratory. This requires proof that the material forming the continuous phase does not change within the range (material B instead of material A is the continuous phase). A disintegration test is required for each continuous phase that occurs. It must be demonstrated using electron microscopy that there is no phase change within the requested range.

Ranges in blends made from 3 different materials:

It is possible to register composition ranges of three different materials that have already been registered. For determining maximum layer thickness, it is sufficient to test the compostability properties of a blend for each continuous phase. Maximum layer thickness can be differentiated depending on the layer thickness tested for the continuous phase.

Provided that the range within the blend remains inside a certain threshold, some of the tests may be omitted. This must be determined in coordination with DIN CERTCO and the testing laboratory. This requires proof that the continuous phase does not change within the range. A disintegration test is required for each continuous phase that occurs. It must be demonstrated using electron microscopy that there is no phase change within the stated range.

Example:

Tests required for a range of a blend of registered materials A, B and C under the assumption that the material with a share of 60 % forms the continuous phase (this shall be evidenced in the certification procedure):

Determination of degradation properties with material A as continuous phase:

$$A/B/C = 60/20/20$$

Determination of degradation properties with material B as continuous phase:

$$A/B/C = 20/60/20$$

Determination of degradation properties with material C as continuous phase:

$$A/B/C = 20/20/60$$

6.2.3 Manufactured items consisting of natural organic substances

If exclusively chemically unmodified constituents of natural origin (e.g. wood, wood fibre, cotton fibre, starch, paper pulp or jute) and admissible for composting according to the applicable legal stipulations are used for the manufactured item, such item are accepted by DIN CERTCO as being biodegradable without testing. The following documents and information must be submitted along with the application form:

- a) Disclosure of chemical composition (including additives at concentrations below 1 % of mass).
- b) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- c) Test report on the chemical characterisation as specified in Section B 1.
- d) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather earthworm toxicity test).
- e) An infrared transmission spectrum in accordance with Section C.

If additives are being used, then the requirements according to 6.2.9 apply accordingly.

6.2.4 Manufactured items consisting of paper/recycled paper

Remark:

In paper industry, fillers are called pigments.

If certification is being requested for a manufactured item consisting of paper/recycled paper, then the following documents and information must be submitted along with the application form:

- a) Disclosure of the paper's chemical composition and structure (including additives at concentrations below 1 % of mass).
- b) Disclosure of the manufactured item's chemical composition (including additives at concentrations below 1 % of mass).
- c) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- d) Test report on the chemical characterisation as specified in Section B 1.
- e) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather earthworm toxicity test).
- f) An infrared transmission spectrum in accordance with Section C.

The requirements according to 6.2.9 apply accordingly for the additives being used.

If using recycled paper, the following additional evidence is required:

- Evidence of continuous compliance with the threshold values according to Table A.1 of DIN EN 13432 via a suitable quality assurance system.
- An additional chemical analysis performed annually according to Section B 1 within the scope of annual control testing according to 5.2.2.

Certification of manufactured items requires information on the maximum layer thickness and grammage. Both additional conditions must be fulfilled.

6.2.4.1 Special rules

The following special rules have been developed to minimise testing expenditures.

Chemical pulp with less than 1 % additives, **without** pigmentation and without use of wet strengtheners:

- For single-sided coating, up to 50 % of the tested layer thickness of the registered polymer and up to 100 % of the tested layer thickness of the paper can be certified/registered without additional tests.
- For double-sided coating, up to 25 % of the tested layer thickness of the registered polymer and up to 100 % of the tested layer thickness of the paper can be certified/registered without additional tests.
- For single-sided coating with 2 different polymers, up to 25 % of the tested layer thickness of each polymer and up to 100 % of the tested layer thickness of the paper can be certified/registered without additional tests.
- For double-sided coating with 2 different polymers, up to 12.5 % of the tested layer thickness of the polymer and up to 100 % of the tested layer thickness of the paper can be certified/registered without additional tests.

Mechanical pulp with less than 1 % additives, **without** pigmentation and without use of wet strengtheners:

- For single-sided coating, up to 50 % of the tested layer thickness of the polymer and up to 50 % of the tested layer thickness of the paper can be certified/registered without additional tests.
- For double-sided coating, up to 25 % of the tested layer thickness of the polymer and up to 50 % of the tested layer thickness of the paper can be certified/registered without additional tests.
- For single-sided coating with 2 different polymers, up to 25 % of the tested layer thickness of each polymer and up to 50 % of the tested layer thickness of the paper can be certified/registered without additional tests.
- For double-sided coating with 2 different polymers, up to 12.5 % of the tested layer thickness of the polymer and up to 50 % of the tested layer thickness of the paper can be certified/registered without additional tests.

Chemical pulp with less than 1 % additives, **with** pigmentation and without use of wet strengtheners:

- For single-sided coating, up to 50 % of the tested layer thickness of the polymer and up to 50 % of the tested layer thickness of the paper can be certified/registered without additional tests.
- For double-sided coating, up to 25 % of the tested layer thickness of the polymer and up to 50 % of the tested layer thickness of the paper can be certified/registered without additional tests.
- For single-sided coating with 2 different polymers, up to 25 % of the tested layer thickness of each polymer and up to 50 % of the tested layer thickness of the paper can be certified/registered without additional tests.

- For double-sided coating with 2 different polymers, up to 12.5 % of the tested layer thickness of the polymer and up to 50 % of the tested layer thickness of the paper can be certified/registered without additional tests.

Recycled paper with less than 1 % additives, without pigmentation and without use of wet strengtheners

The same evaluation rules mentioned above regarding composting properties as for new paper apply.

6.2.5 Manufactured items composed of registered materials and materials indicated in Section A

If certification is being requested for a manufactured item that is intended to contain the fillers and processing auxiliaries indicated in Section A, it is possible to register individual compositions within a predefined composition range. The following documents and information must be submitted along with the application form:

- a) Disclosure of the manufactured item's chemical composition (including additives at concentrations below 1 % of mass).
- b) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- c) The upper limit of 49 % by mass for the proportion of inorganic material and the upper limits specified in Section A for the respective fillers or processing auxiliaries may not be exceeded in the material as a whole.
- d) Safety data sheets according to REACH are to be submitted for all materials used as specified in Section A. Proof of compliance with the requirements of Section B 1 with respect to the heavy metal content must be supplied for each individual filler or processing auxiliary. Alternatively, chemical characterisation according to Section B 1 has to be performed.
- e) Test reports on testing compostability under practice-relevant conditions (disintegration) according to Section B 3.
- f) An infrared transmission spectrum in accordance with Section C.

Should various portions of the materials named in Section A be used, then the test must be performed using the largest portion being included in the application.

Provided no more than 3 % of mass consists of inorganic filling according to Section A, then the disintegration test according to Section B 3 can be omitted.

Within the separate subgroups or sections (as per Section A), other mixtures may, under the following conditions, be registered up to the upper limit documented in the test report:

- In subgroup 1.1 or Sections 1.2.1, 1.2.2 or 1.2.3: Other fillers or mixtures of fillers of the same subgroup or Section can be selected without restriction up to the registered upper limit, e.g. chalk can be replaced by talc without additional disintegration testing. An amendment of the certificate is required.
- In Section 1.2.4 and the subgroups 2.1 and 2.2: Proportions of the tested processing auxiliaries can be selected without restriction up to the registered upper limit, e.g. xylite can be replaced by sorbite without additional disintegration testing. An amendment of the certificate is required.

6.2.6 Manufactured items with coatings

If manufactured items are coated, then the following types must be differentiated:

6.2.6.1 Coating using substances whose biodegradation has not been proven, but have excellent water solubility and are being used in portions less than 1 % of mass

The following documents and information must be submitted along with the application form:

- a) Disclosure of the manufactured item's chemical composition (including additives at concentrations below 1 % of mass).
- b) Data on the coatings layer thickness.
- c) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- d) An infrared transmission spectrum in accordance with Section C.

Evidence of good water solubility can be provided, for example, by the Material Safety Datasheet according to REACH. Alternative evidence is possible and will be evaluated by DIN CERTCO.

6.2.6.2 Coating using substances whose biodegradation has not been proven and are being used in portions less than 1 % of mass

The following documents and information must be submitted along with the application form:

- a) Disclosure of the manufactured item's chemical composition (including additives at concentrations below 1 % of mass).
- b) Data on the coatings layer thickness.
- c) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- d) Test reports on testing compostability under practice-relevant conditions (disintegration) according to Section B 3 of the coated item.
- e) An infrared transmission spectrum in accordance with Section C.

6.2.6.3 Coating using materials whose biodegradation has not been proven and are being used in portions more than 1 % of mass

The following documents and information must be submitted along with the application form:

According to DIN EN 13432, DIN EN 14995:

When using significant organic additives the following tests will be required in addition to the requirements stated under Section 6.2.9.

Testing of additives:

- a) Test report on testing of ultimate biodegradability as specified in Section B 2.

And of the coated manufactured item:

- b) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather earthworm toxicity test). Alternatively the ecotoxicity testing or rather the earthworm toxicity test can be performed on each single substance.
- c) Test report on the chemical characterisation as specified in Section B 1. Alternatively the testing can be performed on each single substance.
- d) An infrared transmission spectrum in accordance with Section C.

Alternatively:

Testing of coated manufactured item according to 6.2.1.

According to ISO 17088, ISO 18606:

When using significant organic additives in portions between 1 and 10 % of mass the following tests will be required in addition to the requirements stated under Section 6.2.9.

Testing of additives:

- a) Test report on testing of ultimate biodegradability as specified in Section B 2.

And of the coated manufactured item:

- b) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather

earthworm toxicity test). Alternatively the ecotoxicity testing or rather the earthworm toxicity test can be performed on each single substance.

- c) Test report on the chemical characterisation as specified in Section B 1. Alternatively the testing can be performed on each single substance.
- d) An infrared transmission spectrum in accordance with Section C.

Alternatively:

When using significant organic additives in portions more than 10 % of mass the testing of the coated manufactured item according to Section 6.2.1 can be carried out alternatively in addition to the requirements stated under Section 6.2.9.

According to AS 4736:

When using significant organic additives in portions more than 1 % of mass the following tests will be required in addition to the requirements stated under Section 6.2.9.

Testing of substances used in portions more than 1 %:

- a) Test report on testing of ultimate biodegradability as specified in Section B 2.

And of the coated manufactured item:

- b) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather earthworm toxicity test). Alternatively the ecotoxicity testing or rather the earthworm toxicity test can be performed on each single substance.
- c) Test report on testing of ultimate biodegradability as specified in Section B 2.
- d) Test report on the chemical characterisation as specified in Section B 1. Alternatively the testing can be performed on each single substance.
- e) An infrared transmission spectrum in accordance with Section C.

6.2.6.4 Coatings with materials that have already been registered with portions over 1 % of mass

The following documents and information must be submitted along with the application form:

- a) Disclosure of the manufactured item's chemical composition (including additives at concentrations below 1 % of mass).
- b) Data on the coatings layer thickness.
- c) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- d) Test reports on testing compostability under practice-relevant conditions (disintegration) according to Section B 3 of the coated item.
- e) An infrared transmission spectrum in accordance with Section C.

6.2.7 Manufactured items consisting of multiple layer structures made of registered materials

If certification is being requested for a manufactured item consisting of multiple layers of materials already on the list according to Section 6.10 and are therefore demonstrated to be compostable (without using auxiliary materials), then the following documents and information must be submitted along with the application form:

- a) Disclosure of the exact structure, including information on coat thickness of the individual coats.
- b) Disclosure of the composition of each layer (including additives at concentrations below 1 % of mass).
- c) Disclosure of other additives used (including additives used at concentrations below 1 % of mass).
- d) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- e) List of the materials used, including information on mass portions.
- f) Test reports on testing compostability under practice-relevant conditions (disintegration) according to Section B 3.
- g) An infrared transmission spectrum in accordance with Section C.

If additives are being used, then each individual layer must fulfil the requirements of this certification scheme regarding biodegradability and the use of additives.

6.2.7.1 Special rules: 2 layers

The following special rules have been developed to minimise testing expenditures.

- Testing according to Section B 3 (disintegration) may be omitted in the case of two-layer structures if the layer thickness of each of the two materials does not exceed half of the maximum compostable material thickness of the individual materials determined by testing in accordance to Section B 3,

or

- if both layers have been manufactured using the same material and the maximum registered thickness of the used material is not exceeded by the two layer structure.

Both the individual layers as well as the overall product must comply with the other requirements in Section 6. These rules apply for laminates and coextrudates, provided no adhesive is being used.

Example:

Material A is registered with a maximum layer thickness of 150 µm.

Material B is registered with a maximum layer thickness of 400 µm.

With a maximum layer thickness of 75 µm for material A and 200 µm for material B and with respecting the other requirements in Section 6, disintegration testing can be omitted.

6.2.7.2 Special rules: 3 layers

The following special rules have been developed to minimise testing expenditures.

For three-layered structures, the test according to Section B 3 (disintegration) can be omitted if

- The overall thickness of the three layered structure does not exceed half of the minimum registered thickness among the three registered materials, as determined in a test according to Section B 3.

or

- All layers have been manufactured using the same material and the maximum layer thickness of the material being used is not exceeded.

These rules apply for laminates and coextrudates, provided no adhesive is being used.

Example:

Material A is registered with a maximum layer thickness of 150 µm.

Material B is registered with a maximum layer thickness of 400 µm

Material C is registered with a maximum layer thickness of 1000 µm.

With a maximum layer thickness of the 3-layer structure of 75 µm and with respecting the other requirements in Section 6, disintegration testing can be omitted.

6.2.7.3 Special rules: multiple layers of the same material

For multiple layered structures where all layers consist of the same registered material (without additives), the test according to Section B 3 (disintegration) can be omitted if the layer thickness of the multiple layer structure does not exceed the maximum registered layer thickness for the material being used.

6.2.8 Manufactured items exceeding the maximum registered/certified layer thickness

If a manufactured item exceeds the maximum registered layer thickness of the material/intermediate/product being used, then the compostability of the manufactured item has to be evidenced separately.

Additional Test required:

Test reports on testing of compostability under practice-relevant conditions according to Section B 3 (disintegration).

Alternatively, a confirmation of acceptability can be issued according to Section 6.3.

6.2.9 Manufactured items consisting of manufactured items already registered/certified and non-biodegradable additives

This can be e.g. a printed shopping bag.

Certification of manufactured items consisting of various alternative materials/intermediates/products is possible provided the certification scheme's requirements have been met for all alternatives.

The other requirements according to Section 6.2 must be met.

6.2.9.1 Use of harmless additives with less than 1 % of mass per additive and less than 5 % of mass of non-biodegradable additives

According to Section A2.1 of DIN EN 13432, A2.1 of DIN EN 14995, 6.3.1 of ISO 17088, 6.3.1 of ISO 18606 and 5.4.2.1 of AS 4736 organic additives whose biodegradability has not been separately determined can be used on the following conditions:

- Less than 1 % of mass per organic additive.
- Less than 5 % of mass in total of organic additives whose biodegradability has not been proven.
- Additives are harmless for the composting process.

Required information/tests/documents:

- a) List of all additives, including portions of mass.
- b) Material Safety Data Sheets according to REACH for all substances being used to determine substances' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- c) An infrared transmission spectrum in accordance with Section C.

6.2.9.2 Using printing inks

It is generally possible to use printing inks. In addition to the requirements named in Section 6.2, the printed product must also comply with the threshold values in Table A.1 of DIN EN 13432.

No more than 1 % of mass of dry printing ink per colour (e.g. red, green, etc) may be used, and a total of no more than 5 % printing ink. Compliance with the thresholds according to Table A.1 in DIN EN 13432 is required.

Additionally, the following documents and information must be submitted along with the application form:

- a) Material Safety Data Sheets according to REACH for all colours (e.g. red, yellow, etc.) being used to determine additives' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- b) For each colour used, information on heavy metal contents in the form of test reports according to Section B 1.

Alternatively: Test report on the chemical characterisation as specified in Section B 1 of a printed product sample. The portions of the individual colours tested here will be defined as maximum useable colours.

If the individual printing inks are tested, then 80 % of the threshold from table A.1 in DIN EN 13432 may not be exceeded with the maximum colour quantity being requested.

If different colours are used, the maximum usable amount will be defined by the colour with the lowest possible concentration.

Example:

The inks A, B and C have been limited to the following amounts according to Section B 1:

- Color A: 0,1 % of mass
- Color B: 0,4 % of mass
- Color C: 0,6 % of mass

The single use of each colour are therefore limited to 0,1 % of mass 0,4 % of mass and 0,6 % of mass, respectively. Is colour A in use the overall amount of printing colour combined is limited to 0,1 %, for the use of colour B (without colour A) 0,4 % only, etc. This is also valid for mixtures of pigments used as printing colours.

6.2.9.3 Use of adhesives

Remark:

This does not refer to registered materials used as adhesive.

If an adhesive is being used with mass portions of less than 1 % of mass, then the following documents and information must be submitted along with the application form:

- a) List of all adhesives being used, along with mass portions and a description of distribution/areas of application.
- b) Material Safety Data Sheets according to REACH for all adhesives being used to determine additives' suitability for composting.

If substances' harmlessness cannot be determined using the Material Safety Data Sheet, then a testing of quality of the compost must be performed according to Section B 3 (e.g. ecotoxicity plant test; additionally earthworm toxicity test if norm conformity to AS 4736 is applied). This is coordinated with DIN CERTCO and, if applicable, with the testing laboratories or the assessment committee.

- c) Test reports on testing of compostability under practice-relevant conditions (disintegration) according to Section B 3 of the manufactured item including the adhesive.

If an adhesives suitability cannot be determined, then a test must be performed under practice-relevant conditions for compostability and compost quality according to Section B 3 (disintegration and ecotoxicity/earthworm toxicity test).

6.2.9.4 Use of additives with more than 1 % of mass per additive and/or more than 5 % of mass of additives

The following documents and information must be submitted along with the application form:

According to DIN EN 13432, DIN EN 14995:

When using significant organic additives the following tests will be required in addition to the requirements stated under Section 6.2.9.

Testing of additives:

- a) Test report on testing of ultimate biodegradability as specified in Section B 2.

And of the manufactured item:

- b) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather earthworm toxicity test). Alternatively the ecotoxicity testing or rather the earthworm toxicity test can be performed on each single substance.
- c) Test report on the chemical characterisation as specified in Section B 1. Alternatively the testing can be performed on each single substance.
- d) An infrared transmission spectrum in accordance with Section C.

Alternatively:

Testing of the manufactured item according to 6.2.1.

According to ISO 17088, ISO 18606:

When using significant organic additives in portions between 1 and 10 % of mass the following tests will be required in addition to the requirements stated under Section 6.2.9.

Testing of additives:

- a) Test report on testing of ultimate biodegradability as specified in Section B 2.

And of the manufactured item:

- b) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather earthworm toxicity test). Alternatively the ecotoxicity testing or rather the earthworm toxicity test can be performed on each single substance.
- c) Test report on the chemical characterisation as specified in Section B 1. Alternatively the testing can be performed on each single substance.
- d) An infrared transmission spectrum in accordance with Section C.

Alternatively:

When using significant organic additives in portions more than 10 % of mass the testing of the manufactured item according to Section 6.2.1 can be carried out alternatively in addition to the requirements stated under Section 6.2.9.

According to AS 4736:

When using significant organic additives in portions more than 1 % of mass the following tests will be required in addition to the requirements stated under Section 6.2.9.

Testing of substances used in portions more than 1 %:

- a) Test report on testing of ultimate biodegradability as specified in Section B 2.

And of the manufactured item:

- b) Test reports on testing of compostability under practice-relevant conditions and of the quality of the compost as specified in Section B 3 (disintegration and ecotoxicity or rather earthworm toxicity test). Alternatively the ecotoxicity testing or rather the earthworm toxicity test can be performed on each single substance.
- c) Test report on testing of ultimate biodegradability as specified in Section B 2.
- d) Test report on the chemical characterisation as specified in Section B 1. Alternatively the testing can be performed on each single substance.
- e) An infrared transmission spectrum in accordance with Section C.

6.2.10 Special cases for Products/Intermediates

6.2.10.1 Design requirements

All polymer materials used in the product must comply with the maximum degradable layer thickness yielded in the test according to Section B 3.

6.2.10.2 Hollow body

In the case of hollow bodies with small diameter apertures, the maximum permissible wall thickness d_{\max} is limited to 50 % of the maximum compostable material thickness determined in accordance with Section B 3 for the material (or intermediate) being used. This applies to all hollow bodies for which the ratio of volume to aperture area yields a value for x greater than 10 cm.

Calculation is based on the following formula:

$$x = \frac{\text{container volume}}{\text{aperture area}}$$

Hollow bodies with $x > 10$ cm, may have wall thicknesses up to d_{\max} , if a test report is submitted on the determination of the maximum compostable material thickness for this product in accordance with Section B 3. Where justified in exceptional cases, the performance of further tests specified in Section B 3 may be required by the assessment committee.

6.2.10.3 Packaging units

Packaging units are distinguished in easily manually separable units and not easily manually separable units.

- Easily separable units (packaging units according to DIN EN 13432).
This refers to products like bottles with lids or yoghurt cups.

These products will be processed as a packaging unit. Both parts must independently show conformity with this certification scheme. Therefore, the calculation of potential additives will be referred to each single unit. Nevertheless, the complete and un-separated packaging unit needs to meet the requirements as well.

- Not manually separable units
This refers to products like labels on packaging. These products will be processed as one unit. Any additives contained are being related to the whole unit.

6.3 Confirmations of acceptability for manufactured items

Upon request, a confirmation of acceptability may be issued for manufactured items (e.g. injection-molded parts such as disposable cutlery) after evaluating the required test reports in accordance with the conditions as specified in this Section.

The confirmation attests that the products concerned are compostable, but that, without mechanical pre-treatment, they will not in all cases disintegrate entirely in the course of a unit processing period in a composting plant. The other requirements of the certification scheme and of the corresponding standards must be met. Confirmation of acceptability does not imply the right to use the compostability mark. Its sole purpose is to facilitate communication between the partners at the various stages of the waste disposal process.

The following documents and information must then be submitted

- a) For conformity assessment, the documents according to Section 6.2 must be attached to the application for confirmation of acceptability. The same requirements apply for certification of manufactured goods.
- b) If non-registered materials are being used, then the test report as specified in Section B 3 must be supplemented - for the purposes of documentation - by a detailed photographic record. A calculation of the weight of the specimens representing the state of degradation reached on completion of the test period specified in the relevant standard is also required.
Alternatively, a report may be submitted on an extended test that continues the composting process until the required level of 90 % degradation has been reached. In addition, recommendations on expedient methods of pre-treatment (e.g. comminution) prior to the composting process may be included in the confirmation of acceptability.

If the application is successful, a confirmation of acceptability will be issued that is valid for 3 years. The confirmation attests that the products concerned are compostable within the meaning of Section 4, but that without mechanical pre-treatment they will not in all cases disintegrate entirely in the course of one process interval at a composting plant.

6.4 Definition of types, subtypes and manufactured item families

Products, intermediates and materials that largely differ from each other in significant properties relevant to certification are defined as types or models. Properties relevant to certification include, for example:

- for products/intermediates:
 - Intended use and or contents.
 - Shapes.
 - Product characteristics beyond differences in dimensions.

For example:

Carrier bags and waste bags are two different types.

Plates and cutlery are two different types.

Packaging for fruits and waste bags are two different types.

Packaging for food and non-food articles are two different types.

- for materials:
 - Chemical structures.
 - Composition.
 - Compositions that cannot be defined as composition range.

Ranges in connection with materials are grouped into one certificate.

An individual certificate will be issued for each type.

A subtype is defined as the (end) product that is different based on dimensions. Multiple alternative subtypes are grouped into one product family of alternative dimensions.

- for products:
 - Dimensions.
 - Materials used.
 - Printing inks or print layouts used.

For example:

Carrier bags made from different materials and with different dimensions are subtypes.

- for materials, half-finished items:
 - Various materials used with the same additives.
 - Percentage differences for various materials used with the same additives.

Multiple subtypes can be grouped onto one certificate.

6.5 Sub-licences

According to DIN CERTCO's General Terms and Conditions, the rules governing logo use and logo usage guidelines, sub-licences are necessary if certified manufactured items are intended to be brought onto the market on behalf of companies other than the main certificate holder.

6.5.1 Sub-licences and without self-production

It is possible to issue sub-licences for all manufactured items as defined in this certification scheme. They facilitate bringing certified manufactured items into circulation on behalf of the sub-licence holder. Sub-licences are dependent upon the validity of the main certificate. Manufactured items may not be changed (e.g. printed) by sub-licence holders. Exceptions to this are packaging seals, batch number printing and best before dates.

Documents and information required for application:

- a) Application form with stamp and signature.
- b) Sub-licence holder's declaration that the main certificate holder's products enter into commercial trade without being changed.
- c) Declaration of confirmation from the main certificate holder that a sub-licence shall be issued.

A sub-licence can be issued

- With its own individual registration number.
- With the main certificate holder's registration number.

6.5.2 Sub-licences for production facilities

Sub-licences for production facilities may be issued for certified/registered manufactured items. They facilitate bringing certified manufactured goods into circulation on behalf of the production facility's owner. Sub-licences are dependent upon the validity of the main certificate. The production facility owner must produce the manufactured items according to the specifications indicated by the holder of the main licence.

An annual verification test must be performed according to Section 7.4.

Documents and information required for application:

- a) Application form with stamp and signature.
- b) Declaration from the production facility operator that the products are being manufactured according to the main certificate's stipulations.
- c) Declaration of consent from the main certificate holder that a sub-licence may be issued.
- d) Forwarding of a datasheet, completely filled out by the production facility operator accordingly.
- e) An infrared transmission spectrum in accordance with Section C for each product.

A sub-licence can be issued

- With its own individual registration number.
- With the main certificate holder's registration number.

6.6 Confidentiality

The members of committees set up to implement this certification scheme are under obligation to observe strict secrecy. The members of all participating bodies further undertake by signing a declaration of commitment not to pass on to third parties any information on products and companies they may obtain in connection with their certification activities.

6.7 Conformity assessment

On the basis of the documents submitted, DIN CERTCO conducts the conformity examination. The assessment is made with the aid of the test report as to whether the product meets the requirements of the certification scheme and of the underlying standards.

The applicant will receive written notification from DIN CERTCO in the event of any possible deviations.

6.8 Registration numbers of products, materials, intermediates and confirmations of acceptability

Composition of the registration number:

- | | |
|----------------------------------|--------|
| – Products | 9Gxxxx |
| – Materials | 9Kxxxx |
| – Intermediates | 9Lxxxx |
| – Confirmations of acceptability | 9Uxxxx |

6.9 Certificate and the right to use the mark for (end)products

After successful testing and conformity assessment of the application documents submitted, DIN CERTCO issues a certificate to the applicant and issues the right to use the compostability mark "DIN-Geprüft Industrial Compostable" for products in conjunction with the respective registration number.



Products made of compostable materials for which a right to use the compostability mark "DIN-Geprüft Industrial Compostable" has been issued must be marked with the "DIN-Geprüft Industrial Compostable"-Logo and the respective registration number.

Logo and registration number may only be used for the product/material/intermediate for which the certificate has been issued and that corresponds to the type-tested product/material/intermediate.

For each respective type, a registration number shall be issued. For design types (sub-types) of a type, the same registration number shall be issued (for information, see Section 6.4).

Materials and intermediates do **only** receive the right to use the mark for **marketing and advertising purposes**. They are certified and receive registration numbers (9Kxxx or 9Lxxx). For each respective type, a registration number shall be issued. For design types (sub-types) of a type, the same registration number shall be issued (for information, see Section 6.4).

Sub-certificate holder gain the same right to use the mark as the main certificate holder regardless of whether an own registration number has been issued.

The General Terms and Conditions of DIN CERTCO also apply.

6.10 Publication

All certificate holders can be viewed on the daily up-dated homepage of DIN CERTCO (www.dincertco.de) under <Certificates and Registrations>. Manufacturers, users and consumers use this research possibility for obtaining information on certified products.

Besides the contact details of the certificate holders (telephone, telefax, e-mail, homepage), it is also possible to view the technical data regarding dimensions and maximum layer thicknesses for the certified product and registered intermediate or material.

6.11 Validity of certificates and confirmations of acceptability

The certificate for products is valid for 3 years. The period of validity is shown on the certificate. On expiry of the certificate, the right to use the mark also expires.

The confirmation of acceptability for products, intermediates and materials is valid for 3 years. The period of validity is shown on the confirmation of acceptability.

The certificate for intermediates and materials is valid for 6 years. The period of validity is shown on the certificate.

6.12 Renewal of certificates and confirmations of acceptability

If the validity of certification or acceptability confirmation is to remain valid beyond the date indicated, an application for renewal must be submitted to DIN CERTCO sufficiently in advance prior to validity expiring.

The manufactured item's current composition must be submitted with the application for renewal. For renewals, DIN CERTCO will make an assessment based on the certification scheme valid at the time of renewal and may request supplemental documentation.

Furthermore, if no deviations were found during the three verification tests performed within the validity, the certificate may be renewed.

6.13 Expiration of certificates and confirmations of acceptability

In the event that the new standard conformity examination according to Section 5 has not been completed before expiration of the validity period, the certificates and/or confirmations of acceptability and the registration number expires without the necessity for explicit notification from DIN CERTCO.

Furthermore, certificates and confirmations of acceptability can expire if, for example:

- the surveillance according to Section 7 is not performed punctually or completely.
- the compostability mark “DIN-Geprüft Industrial Compostable” is misused by the certificate holder.
- the requirements laid down in the certification scheme or its accompanying documents are not fulfilled.
- the certification fees are not paid on the due date.
- the prerequisites for the issuing of the certificate or confirmation of acceptability are no longer fulfilled.

6.14 Alterations/Amendments

6.14.1 Alteration/Amendment to a product, intermediate or material

The certificate holder is obliged to notify DIN CERTCO of all alterations to the manufactured item without delay. DIN CERTCO will, if applicable, decide in coordination with the assessment committee the extent to which testing according to Section 5.2.3 must be performed and whether the change is significant. The respective test report shall be forwarded to DIN CERTCO by the test laboratory.

Should the testing laboratory determine a substantial alteration, the certificate with the corresponding registration number shall expire. For the modified manufactured item, a new application for initial certification authorising the use of the compostability mark or initial issuance of a confirmation of acceptability may be submitted.

The certificate holder remains obliged to notify of any changes in the formal details (e.g. name of certificate holder or his address). For this purpose an application for amendment must be sent to DIN CERTCO. The certificate will be changed respectively.

The certificate holder may apply to DIN CERTCO for an extension of the existing certificate /confirmation of acceptability for further design-types (sub-types) of the same type. It is for DIN CERTCO to decide whether these amendments require a complementary examination. The design-types shall be entered in the certificate /confirmation of acceptability for the already certified product and, provided that the conditions are fulfilled, shall be regarded as an integral part of same.

6.14.2 Alterations to the basic test specifications

If the basic test specifications for the certification are modified, an application for the alteration of the certification shall be generally submitted within 6 months of receiving notification from DIN CERTCO, and ,as a rule, after 12 months, proof of conformity with the modified examination specifications shall be submitted in the form of a positive test report, if applicable (see Section 5.5).

The time limit will be defined by DIN CERTCO and might last up to the next renewal at the latest.

6.15 Defects in products, intermediates, materials

In the event that a certified product on the market is found to be defective, the certificate holder shall be summoned in writing by DIN CERTCO to rectify the defects.

In conjunction with the testing laboratory, DIN CERTCO shall decide whether it is a serious or a minor defect.

In the case of defects having a direct or indirect effect on the degradation properties (serious defects), the manufacturer must ensure that, until the defects have been rectified, the products are no longer marked with the mark of conformity.

The defects must also be rectified without delay in installed products or products in storage. The manufacturer must submit proof to DIN CERTCO within 3 months, in the form of a test report on a special test in accordance with Section 5.2.4, that the defects have been rectified and that the product in question again fulfils the stipulated requirements.

In the case of defects that have no influence on the technical safety or functionality of the product (minor defects), the manufacturer must submit suitable proof to DIN CERTCO within 3 months that the defects in the product in question have been rectified.

Should the manufacturer fail to observe these deadlines, he and the distributor of product will no longer be permitted to use the compostability mark.

Should grounds for complaint continue to exist, DIN CERTCO shall initially suspend the certificate and at the same time issue a final deadline for the rectification of the defects. Should the certificate holder fail to meet this demand, or fail to meet it within the grace period, or if it is again not possible to prove that the defects have been rectified, the certificate shall be annulled.

For holders of certificates for intermediates or materials, the measures named above will apply to the effect that certificates can no longer be acquired and delivery may no longer be made to certified buyers.

7 Surveillance

7.1 General

The constant surveillance of the certified product or the registered material or intermediate is an integral component of the certification itself.

7.2 Surveillance by the manufacturer

The manufacturer must ensure, by suitable quality management measures, that the product characteristics confirmed by the certification are maintained. This can be accomplished by means of an in-house factory production control (FPC) focussed on the product itself or on the production and, in addition, can be guaranteed within the framework of a quality management system (QM-System) in accordance with the standard series DIN EN ISO 9000 ff.

7.3 Surveillance by DIN CERTCO

DIN CERTCO examines the conformity of the product with the requirements laid down in the certification scheme

The costs incurred in such tests will be charged to the certificate holder on their completion.

In individual cases, supplemental tests may be defined within the scope of certification.

7.4 Verification tests (Control tests)

7.4.1 Products

The verification shall be performed at regular intervals of one year.

If production is being carried out at multiple production facilities, the following additional requirements shall apply:

- The control test is performed on products from various production facilities. If there are 3 alternative production facilities, then one sample must be alternately submitted from each production facility for the control test. If there are more than 3 alternative production facilities, then samples must be submitted on an alternating basis of \sqrt{n} of the production facilities for the control test. The number is rounded up to the next integer digit.
- Samples are to be additionally marked with information regarding the corresponding production facility.

The control test covers the following:

- a) Check of identification of product with compostability mark and corresponding registration number according to the logo usage rules.
- b) Check of compliance with the certified maximum admissible wall/layer thickness (d_{max}), density and/or grammage using the samples submitted.
- c) Checking whether all polymeric materials, intermediates and additives used in manufacturing the product and present in the product to a percentage by mass greater than 1 % are identical with those specified in the type testing.

- d) For this purpose, one of the 5 submitted samples is used to perform an infrared transmission spectrum according to Section C. Evidence is demonstrated by comparing the results of the spectral analysis submitted during type testing with the results of the spectral analysis for control testing. When compared, the spectra must show that the two sets of polymeric materials, intermediate and/or additives are identical to the polymer materials or intermediates and additives from type testing.
- e) Performance of one chemical characterisation according to Table A.1 of DIN EN 13432 during the validity.
- f) When using recycled paper, the performance of a chemical analysis according to Section B 1 (see Section 6.2.4.) is required annually.

7.4.2 Materials/Intermediates

The verification shall be performed at regular intervals of two years.

If manufactured items are being produced at multiple production facilities, the following additional requirements shall apply:

- The control test is performed on manufactured items from various production facilities. If there are 3 alternative production facilities, then one sample must be alternatingly submitted from each production facility for the control test. If there are more than 3 alternative production facilities, then samples must be submitted on an alternating basis from \sqrt{n} of the production facilities for the control test. The number is rounded up to the next integer digit.
- Samples are to be marked only with the information regarding the corresponding production facility.

The control test covers the following:

- a) Written confirmation from the manufacturer that composition has not been changed since initial certification.
- b) Check of compliance with the certified maximum admissible wall/layer thickness (d_{\max}) using the samples submitted (if applicable).
- c) Checking whether all polymeric materials, intermediates and additives used in manufacturing the product and present in the product to a percentage by mass greater than 1 % are identical with those specified in the type testing. An infrared transmission spectrum according to Section C from one of the submitted 5 samples is used for this purpose. Evidence is demonstrated by comparing the results of the spectral analyses submitted during type testing with the results of the spectral analyses for control testing. When compared, the spectra must show that the two sets of polymeric materials or intermediates and additives are identical to the polymer materials or intermediates and additives from the type testing.
- d) Performance of one chemical analysis according to Table A.1 of DIN EN 13432 during the validity.
- e) When using recycled paper, it will also be necessary to perform a chemical analysis according to Section B 1 (see Section 6.2.4) every two years.

If a manufacturer has certificates for different manufactured items with identical compositions beside colours, then a control test on one manufactured item will be sufficient. In case that a certification for one or more final product(s) based on self-owned certificates exists at the same time, the verification testing needs to be performed on each type according to Section 7.4.1.

7.5 Assessment of verification test (Control test)

7.5.1 General

The conformity requirements which are tested during verification test have to be fulfilled basically.

7.5.2 Design requirements

If non-conformities are established during testing for compliance with the maximum permissible wall thicknesses according to Section 7, the remaining 4 samples must also be tested. At least 4 of the 5 tested samples of the certified product must meet the specified requirements.

If the criteria are met by fewer than 4 samples, another 10 samples will be tested immediately. If at least 9 of the 10 samples tested comply with the requirements of the certification scheme applying at the time when the certificate was issued, then no complaint will be made.

7.5.3 Spectra (Identification of material)

If deviations from the spectral analyses submitted with the application are established while comparing spectral analyses from the tested samples, then the customer will be requested to send a written statement. If no positive assessment can be reached on the basis of that position statement, then new samples must be submitted for testing.

7.5.4 Complaints

If the requirements according to Section 7.5 are not met after the re-test, the validity of the certificate will be suspended. The certificate holder will be informed immediately and requested to ensure compliance with the criteria within 3 months after receipt of such notice.

While the certificate is suspended, the certificate holder is not entitled to sell manufactured items as certified/registered ones.

If a complaint is made, the control test will be repeated within 3 months. If this re-test yields no further cause for complaint, the certificate will be set valid again. Should reason for complaints continue to exist, the certificate will be cancelled. The latest re-test named will not apply as a regular control test, but rather as a special test for which the certificate holder must cover the costs.

A Fillers, colours and processing auxiliaries

Materials that may be used in varying proportions up to the given upper limits as additives in manufacturing or processing of compostable materials according to Section 6.2.5.

Main Group 1: Fillers

Subgroup 1.1: Inorganic fillers and pigments - admixture up to a maximum of 49 %

- Aluminium silicates
- Ammonium carbonate
- Calcium carbonate
- Calcium chloride
- Dolomite
- Iron oxides (pigment)
- Gypsum
- Mica
- Graphite (pigment)
- Kaolin
- Chalk
- Sodiumcarbonate
- Natural silicates
- Carbon black (pigment)
- Silicon dioxide; quartz
- Talc
- Titanium dioxide (pigment)
- Wollastonite

Subgroup 1.2: Organic fillers - admixture up to a maximum of 49 %

Section 1.2.1: Non- modified native cellulose

- Vegetable fibers

Section 1.2.2: Non-modified native Ligno-Cellulose

- Wood flour/wood fibers
- Vegetable fibers
- Cork
- Bark

Section 1.2.3: Non-modified natural starch

- Starch
- Rye flour and other flours

Section 1.2.4: Miscellaneous

- Starch acetate (up to a substitution level of 1.6)

Main Group 2: Processing auxiliaries**Subgroup 2.1: Processing auxiliaries - admixture up to a maximum of 10 %**

- Benzoic acid/sodium benzoate
- Euristic amide/euristic amide
- Glycerol monostearate
- Glycerol monooleate
- Natural waxes
- Polyethylene glycol (up to molecular weight 2000)
- Stearates

Subgroup 2.2: Processing auxiliaries - admixture up to a maximum of 49 %

- Glycerin/glycerol
- Sorbitol
- Citric acid ester (with linear, aliphatic chains up to a chain length of C22)
- Glycerol acetates
- Xylitol

B Tests**B 1 Chemical characterisation****B 1.1 According to DIN EN 13432, DIN EN 14995, ISO 17088, ISO 18606 or AS 4736**

The chemical test is conducted in accordance with the requirements of DIN EN 13432.

B 2 Testing of ultimate biodegradability

Table 1 Overview about the test methods depending on the standard which is applied for

Testing may be performed in accordance with the following standards	DIN EN 13432 (mandatory)	DIN EN 14995	ISO 17088	ISO 18606	AS 4736
ISO 14855-1	x	x	x	x	x
ISO 14855-2			x	x	
ISO 14851	x*	x*		x*	x*
ISO 14852	x*	x*		x*	x*
ASTM D 5338			x		
DIN EN 14046	x				

* Only possible if the nature and properties of the test material do not permit testing to ISO 14855-1.

B 2.1 As specified in DIN EN 13432

Testing of ultimate biodegradability is conducted in accordance with the criteria of DIN EN 13432 by one of the following methods:

- DIN EN ISO 14855-1 "Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions -- Method by analysis of evolved carbon dioxide -- Part 1: General procedure"
- DIN EN 14046 "Packaging - Evaluation of the ultimate aerobic biodegradability of packaging materials under controlled composting conditions - Method by analysis of released carbon dioxide"

Alternatively, one of the following methods can be used:

- ISO 14851 "Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium – Method by measuring the oxygen demand in a closed respirometer"
- ISO 14852 "Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium – Method by analysis of evolved carbon dioxide"

B 2.2 As specified in DIN EN 14995

If the type and properties of the material being tested permit, the controlled aerobic composting test according to EN ISO 14855 must be applied:

DIN EN ISO 14855-1 "Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions -- Method by analysis of evolved carbon dioxide - Part 1: General procedure"

If alternative methods are necessary, then the following methods can be used:

- ISO 14851 "Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium – Method by measuring the oxygen demand in a closed respirometer"
- ISO 14852 "Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium – Method by analysis of evolved carbon dioxide"

B 2.3 As specified in ISO 17088

Testing of ultimate biodegradability is conducted in accordance with the criteria of ISO 17088 by one of the following methods:

- DIN EN ISO 14855-1 "Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions -- Method by analysis of evolved carbon dioxide - Part 1: General procedure"
- DIN EN ISO 14855-2 "Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions -- Method by analysis of evolved carbon dioxide - Part 2: Gravimetric measurement of carbon dioxide evolved in a laboratory-scale test"
- ASTM D 5338 "Standard Test Method for Determining Aerobic Biodegradation of Plastics Materials Under Controlled Composting Conditions"

B 2.4 As specified in ISO 18606

Testing of ultimate biodegradability is conducted in accordance with the criteria of ISO 18606 by one of the following methods:

- DIN EN ISO 14855-1 "Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions -- Method by analysis of evolved carbon dioxide - Part 1: General procedure"
- DIN EN ISO 14855-2 "Determination of the ultimate aerobic biodegradability of plastic materials under controlled composting conditions -- Method by analysis of evolved carbon dioxide - Part 2: Gravimetric measurement of carbon dioxide evolved in a laboratory-scale test"

If alternative methods are necessary, then the following methods can be used:

- ISO 14851 "Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium – Method by measuring the oxygen demand in a closed respirometer"
- ISO 14852 "Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium – Method by analysis of evolved carbon dioxide"

B 2.5 As specified in AS 4736

If the type and properties of the material being tested permit, the controlled aerobic composting test according to EN ISO 14855 must be applied.

If alternative methods are necessary, then the following methods can be used:

- ISO 14851 "Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium – Method by measuring the oxygen demand in a closed respirometer"
- ISO 14852 "Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium – Method by analysis of evolved carbon dioxide"

B 3 Testing of compostability under practice-relevant conditions and of the quality of the composts

B 3.1 As specified in DIN EN 13432

Compostability under practice-relevant conditions (disintegration):

The following methods are available for testing ultimate compostability under practice-relevant conditions in accordance with DIN EN 13432:

- Testing in a pilot-scale test
- Testing in a composting plant under real conditions

The standard DIN EN 13432 indicates the criteria for a successful test under Section A.4, but it does not prescribe a specific method for the practical performance of the test.

The following test methods can be used for testing in a pilot-scale test:

- ISO 16929 "Plastics - Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test"
- DIN EN 14045 "Packaging - Evaluation of the disintegration of packaging materials in practical oriented tests under defined composting conditions"; German version EN 14045

Maximum compostable layer thickness must be determined in all cases. The optical quality of the compost prepared from biodegradable materials may not be significantly poorer than that of normal compost (testing in accordance with Methodenhandbuch zur Analyse organischer Düngemittel, chapter II, No. C1 und C3).

In addition, physico-chemical parameters must be determined according to Section 8.2 of DIN EN 13432.

The following test methods do not meet the certification scheme's requirements:

- Tests on a laboratory scale, for example according to DIN EN ISO 20200 "Plastics - Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test" (ISO 20200:2004); German edition EN ISO 20200
- Qualitative disintegration tests based on ISO 16929 or DIN EN 14045

Determining compost quality (ecotoxicity):

The criteria for the quality of composts are assessed according to Section 8, A.4 and E of DIN EN 13432 by way of a test of the ecological toxicity with not less than two types of plants. According to ISO 16929, the addition of 10 % testing material to the disintegration testing is necessary. The basis of determination is the (modified) OECD Guideline 208.

To assure the quality of the blank compost, the respective criteria of the OECD Guideline 208 are to be applied:

1. min. 2 weeks after 50 % of the seedlings in the control have emerged, plants are harvested and weighted
2. Validity: min. 80 % of control seeds should produce healthy seedlings

Derivating from the standard, the use of minimum 50 seeds per replicate is required, if the test is performed using barley.

It is possible to test theoretical samples.

B 3.2 As specified in DIN EN 14995

Compostability under practice-relevant conditions (disintegration):

The following methods are available for testing ultimate compostability under practice-relevant conditions in accordance with DIN EN 14995:

- Testing in a pilot-scale test
- Testing in a composting plant under real conditions

The following test methods can be used for testing in a pilot-scale test:

- ISO 16929 "Plastics - Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test"

Maximum degradable layer thickness must be determined in all cases. The optical quality of the compost prepared from biodegradable materials may not be significantly poorer than that of normal compost (testing in accordance with Methodenhandbuch zur Analyse organischer Düngemittel, chapter II, No. C1 und C3).

In addition, physico-chemical parameters must be determined according to Section 8.2 of DIN EN 13432.

The following test methods do not meet the certification scheme's requirements:

- Tests in a laboratory scale, for example according to DIN EN ISO 20200 "Plastics - Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test "
- Qualitative disintegration tests based on ISO 16929 or DIN EN 14045

Determining compost quality (ecotoxicity):

The criteria for the quality of composts are assessed according to Section 8, A.4 and E of DIN EN 13432 by way of a test of the ecological toxicity with not less than two types of plants. According to ISO 16929, the addition of 10 % testing material is necessary. The basis of determination is the (modified) OECD Guideline 208.

To assure the quality of the blank compost, the respective criteria of the OECD Guideline 208 are to be applied:

1. min. 2 weeks after 50 % of the seedlings in the control have emerged, plants are harvested and weighted
2. Validity: min. 80 % of control seeds should produce healthy seedlings

Derivating from the standard, the use of minimum 50 seeds per replicate is required, if the test is performed using barley.

It is possible to test theoretical samples.

B 3.3 As specified in ISO 17088

Compostability under practice-relevant conditions (disintegration):

The following test methods can be used for testing in a pilot-scale test:

- ISO 16929 "Plastics - Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test"

Maximum degradable layer thickness must be determined in all cases. The optical quality of the compost prepared from biodegradable materials may not be significantly poorer than that of normal compost (testing in accordance with Methodenhandbuch zur Analyse organischer Düngemittel, chapter II, No. C1 und C3).

In addition, physico-chemical parameters must be determined according to Section 8.2 of DIN EN 13432.

The following test methods do not meet the certification scheme's requirements:

- Tests in a laboratory scale, for example according to DIN EN ISO 20200 "Plastics - Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test"
- Qualitative disintegration tests based on ISO 16929 or DIN EN 14045

Determining compost quality (ecotoxicity):

The criteria for the quality of composts are assessed according to Section 8, A.4 and E of DIN EN 13432 by way of a test of the ecological toxicity with not less than two types of plants. According to ISO 16929, the addition of 10 % testing material is necessary. The basis of determination is the (modified) OECD Guideline 208.

To assure the quality of the blank compost, the respective criteria of the OECD Guideline 208 are to be applied:

1. min. 2 weeks after 50 % of the seedlings in the control have emerged, plants are harvested and weighted
2. Validity: min. 80 % of control seeds should produce healthy seedlings

It is possible to test theoretical samples.

Derivating from the standard, the use of minimum 50 seeds per replicate is required, if the test is performed using barley.

B 3.4 As specified in ISO 18606

Compostability under practice-relevant conditions (disintegration):

The following test methods can be used for testing in a pilot-scale test:

- ISO 16929 "Plastics - Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test"

Maximum degradable layer thickness must be determined in all cases. The optical quality of the compost prepared from biodegradable materials may not be significantly poorer than that of normal compost (testing in accordance with Methodenhandbuch zur Analyse organischer Düngemittel, chapter II, No. C1 und C3).

Additionally the physico-chemical parameters according to Section 8.2 of EN 13432 standard must be determined.

The following test methods do not meet the certification scheme's requirements:

- Tests in a laboratory scale, for example according to DIN EN ISO 20200 "Plastics - Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test"
- Qualitative disintegration tests based on ISO 16929 or DIN EN 14045

Determining compost quality (ecotoxicity):

The criteria for the quality of composts are assessed according to Section 8, A.4 and E of DIN EN 13432 by way of a test of the ecological toxicity with not less than two types of plants. According to ISO 16929, the addition of 10 % testing material is necessary. The basis of determination is the (modified) OECD Guideline 208.

To assure the quality of the blank compost, the respective criteria of the OECD Guideline 208 are to be applied:

1. min. 2 weeks after 50 % of the seedlings in the control have emerged, plants are harvested and weighted
2. Validity: min. 80 % of control seeds should produce healthy seedlings

Derivating from the standard, the use of minimum 50 seeds per replicate is required, if the test is performed using barley.

It is possible to test theoretical samples.

B 3.5 As specified in AS 4736

Compostability under practice-relevant conditions (disintegration):

The following test methods can be used for testing in a pilot-scale test:

- ISO 16929 "Plastics - Determination of the degree of disintegration of plastic materials under defined composting conditions in a pilot-scale test"

Maximum degradable layer thickness must be determined in all cases. The optical quality of the compost prepared from biodegradable materials may not be significantly poorer than that of normal compost (testing in accordance with Methodenhandbuch zur Analyse organischer Düngemittel, chapter II, No. C1 und C3).

In addition, physico-chemical parameters must be determined according to Section 8.2 of DIN EN 13432.

The following test methods do not meet the certification scheme's requirements:

- Tests in a laboratory scale, for example according to DIN EN ISO 20200 "Plastics - Determination of the degree of disintegration of plastic materials under simulated composting conditions in a laboratory-scale test"
- Qualitative disintegration tests based on ISO 16929 or DIN EN 14045

Determining compost quality (plant ecotoxicity test):

The criteria for the quality of composts are assessed according to Section 8, A.4 and E of DIN EN 13432 by way of a test of the ecological toxicity with not less than two types of plants. According to ISO 16929, the addition of 10 % testing material is necessary. The basis of determination is the (modified) OECD Guideline 208.

To assure the quality of the blank compost, the respective criteria of the OECD Guideline 208 are to be applied:

1. min. 2 weeks after 50 % of the seedlings in the control have emerged, plants are harvested and weighted
2. Validity: min. 80 % of control seeds should produce healthy seedlings

It is possible to test theoretical samples.

Derivating from the standard, the use of minimum 50 seeds per replicate is required, if the test is performed using barley.

Determining compost quality (earthworm toxicity test):

The criteria for the quality of composts are assessed according to ASTM E 1676 by way of a 14-day *Eisenia Fetida* earthworm toxicity test. According to DIN EN 13432, Sections 8, A.4 and E, the addition of 10 % testing material is necessary.

In addition to the requirements defined in ASTM E 1676 the respective criteria are to be applied:

1. Blank compost needs to reach at least 90 % of the result of the reference substrate.
2. At least 90 % of the number and mean weight of the respective living worms used in the blank compost shall be traceable.

C Infrared transmission spectrum

The spectrum should be recorded in a range between the wave numbers 4000 cm^{-1} and 400 cm^{-1} , and a transmission level from 0-100 % being indicated on the vertical axis.